

OPHTEIS

Cohesive

NaHA 1.0%

OPHTEIS+

Highly Cohesive

NaHA 1.4%

OPHTEISMAX

Visco-Adaptive

NaHA 2.5%



 Rayner

With Ophteis, Ophteis+ and OphteisMAX, Rayner offers a complete range of ophthalmic viscosurgical devices (OVD) made from hyaluronic acid of animal origin. The specific combination of different concentrations of HA and a high molecular weight has led to three distinct products with exemplary and complementary pseudoplastic qualities. The range manufactured in Sweden offers an optically clear OVD with no bubbles and can be stored at room temperature.

OPHTEIS

Cohesive • Designed for each stage of cataract surgery

- High molecular weight resulting in high viscosity and pseudoplasticity.
- High cohesion, meaning that it creates space, stabilizes the eye and facilitates movement of tissue.
- High pseudoplasticity enables easy and controlled injection and IOL implantation.
- Easy to remove as a single mass at the end of surgery.

OPHTEIS+


Highly Cohesive • Designed for difficult cases

- Super high molecular weight, pseudoplasticity and cohesion provides maximum intraocular stability, while creating space during capsulorhexis.
- Reliable in more difficult cases such as trauma and refractive surgery.
- Excellent performance during IOL implantation.
- Super high pseudoplasticity provides a product easy to inject and is removed as a single mass after surgery.

OPHTEISMAX

Visco-Adaptive • Designed to adapt to the different stages of surgery

- Viscoadaptive; at rest, it adopts cohesive characteristics (e.g. during capsulorhexis), and under stress it behaves in a dispersive way (e.g. during phacoemulsification).
- Excellent all round product that can also be used for advanced cases and trauma.
- Combines both high and low molecular weight hyaluronic acid.
- Easy to remove as a single mass at the end of surgery.



Product	Ophteis	Ophteis+	OphteisMax
Polymer Origin	Animal origin	Animal origin	Animal origin
Sodium Hyaluronate Concentration	1%	1.4%	2.5%
Molecular Weight (Dalton)	avg. 5 million	avg. 5 million	avg. 4 million
Zero Shear Viscosity (mPas)	avg. 1 million	avg. 3.3 million	avg. 1 million
Osmolality (mOsm/kg)	310	320	360
pH	6.8 - 7.6	6.8 - 7.6	6.8 - 7.6
Shelf life (years)	3	3	3
Storage	2 to 25°C	2 to 25°C	2 to 25°C
Syringe volume (ml)	0.55 / 0.85	0.55 / 0.85	0.85
Cannula (gauge)	27G	27G	25G



GLOBAL HQ & UK OFFICE
RAYNER INTRAOCULAR LENSES LIMITED
 10 Dominion Way
 Worthing, West Sussex
 BN14 8AQ, United Kingdom

Tel: +44 (0) 1903 258 900
 Email: iol_enquiries@rayner.com
 Web: rayner.com

UK CUSTOMER SERVICE
 Tel: +44 (0) 1903 854 560
 Email: orders@rayner.com

GERMANY CUSTOMER SERVICE
 Tel: +49 30 6290783 - 0
 Email: info.de@rayner.com

ITALY CUSTOMER SERVICE
 Tel: +39 800 972485
 Email: commerciale@rayner.com

SPAIN CUSTOMER SERVICE
 Tel: +34 910 480055
 Email: atcliente@rayner.com

Regulatory restrictions may apply in certain markets.
 ©2018 Rayner Intraocular Lenses Limited.
 Ophteis is a registered mark of Rayner. EC 2018-05 01/18